

UNI LL 5,0 mm

Characteristics EN 1817	Standard	Unit	Requirements	Average values from production
Hardness	ISO 48-4 (ISO 7619)	shore A	≥ 75	86
Residual indentation	EN/ISO 24343-1 (EN 433)	mm	≤ 0,20	0,10
Abrasion resistance	ISO 4649 (Met. A - 5N)	mm ³	≤ 250	150
Dimensional stability	EN/ISO 23999 (EN 434)	%	± 0,40 max	± 0,30
Flexibility	EN/ISO 24344 Met. A Ø 20mm (EN 435)	-	no fissuring	comply
Colour fastness to artificial light	ISO 105-B02 Met. 3	degree	≥ 6 blue scale ≥ 3 grey scale	comply
Cigarette burn	EN 1399	rating	met. A ≥ 4 met. B ≥ 3	comply
Characteristics EN 14041				
Fire behaviour	EN 13501-1	class	-	Bfl – s1
Slip resistance	EN 13893	class	≥ 0,30 (DS)	DS
Other characteristics				
Resistance to stains	EN/ISO 26987 (EN 423)	-	-	resistant *
Ramp slip resistance	DIN 51130	°	BGR 181	R9
Thermal resistance and Thermal conductivity	EN 12667	m ² K/W W/mK	-	0,030 0,17
Electrical resistance	EN 1081 Met. A	ohm	-	> 10 ¹⁰
Electrostatic charge	EN 1815	kV	-	≤ 2 (antistatic)
Reduction of sound due to treading	ISO 10140-3	dB	-	up to 16
Castor chairs	EN/ISO 4918 (EN 425)	-	-	suitable for W castors

* depending on concentration and time of contact, for specific agent please ask.



CE EN 14041 DoP_005



5,0 mm




8,3 kg/m²



61 x 61 cm

Classification EN ISO 10874 (EN 685):



The data declared by the manufacturer shall be taken as average: single values change amongst batches and colours.
Artigo reserves the right to change product characteristics at any time. Rev. 1/21